

Dia	Contract	Cylinder	Strength	Required	Age	Made	Tested	Design
4	P922	133 D	5372	3000	4	1/25/2018	1/29/2018	18083
4	R048	120 C	4059	4000	7	1/22/2018	1/29/2018	17259
4.011	R237	6	5800	3000	44	12/13/2017	1/29/2018	16457
4	R237	6A	5928	3000	44	12/13/2017	1/29/2018	16457
4.016	P079	246B	2826	3000	7	1/23/2018	1/30/2018	16627
4	R149	5 C	4189	3000	8	1/23/2018	1/31/2018	16440
4	R048	121 B	4855	4000	8	1/23/2018	1/31/2018	17259
4	R048	121 C	5302	4000	8	1/23/2018	1/31/2018	17259
4	Q340	12	8090	3000	43	12/19/2017	1/31/2018	15524
4	Q340	12A	8077	3000	43	12/19/2017	1/31/2018	15524
4	P922	133 E	6079	3000	7	1/23/2018	2/1/2018	18083
4	M950	718 C	5093	4000	7	1/25/2018	2/1/2018	15519
4	Q076	97 A	5151	3000	28	1/4/2018	2/1/2018	16225
4	Q076	97 A	6122	3000	28	1/4/2018	2/1/2018	16225
4	Q374	16B	4022	3000	2	1/4/2018	2/1/2018	15498
4	Q374	16C	3979	3000	2	1/4/2018	2/1/2018	15498
4.016	Q076	98A	5197	3000	28	1/5/2018	2/2/2018	16225
4	Q076	98A	5361	3000	28	1/5/2018	2/2/2018	16225
4	R149	6C	4151	3000	7	1/26/2018	2/2/2018	16440
4	P079	248B	3943	3000	7	1/26/2018	2/2/2018	16627